

TECHNICAL PRODUCT SHEET

Article FOREVER		Collection	Fabric group	CUSTOMS CODE 55122990
---------------------------	--	------------	--------------	--------------------------

FABRIC TYPE

- Fabric for decoration
 Fabric for upholstery
 Fabric for curtains

TYPE OF MANUFACTURING PROCESS

- | | | |
|--|--|---|
| <input type="checkbox"/> Fibre dyed | <input type="checkbox"/> Yarn dyed | <input checked="" type="checkbox"/> Solution dyed |
| <input type="checkbox"/> Cylinder printing | <input type="checkbox"/> Screen printing | <input type="checkbox"/> Digital printing |
| <input type="checkbox"/> Application | <input type="checkbox"/> Corosion | <input type="checkbox"/> Coating |
| <input type="checkbox"/> Embossing | <input type="checkbox"/> Embroidery | <input type="checkbox"/> Laser |
- DYES**
- | | | |
|---|------------------------------------|---------------------------------|
| <input type="checkbox"/> Direct | <input type="checkbox"/> Reactive | <input type="checkbox"/> Acid |
| <input type="checkbox"/> Pre-metallised | <input type="checkbox"/> Dispersed | <input type="checkbox"/> Others |

RECOMMENDED CLEANING INSTRUCTIONS



DESCRIPTIVE FEATURES

Origin of fabric	<input checked="" type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	100% PAN	Weave _____
Warp repeat cm	↕ _____	Weft repeat cm ← _____
Weight linear mt.	410	Weight sq. metre 270
Average roll length mt.	_____	Minimum roll length mt. _____
Fabric width with selvedge cm.	_____	Fabric width without selvedge cm _____
		Useable width cm 152
		<small>COL. 3 e 8 ALT. 148</small>

DIMENSIONAL STABILITY

	Warp	Weft	
Steam iron	<u>110° C</u>	<u>1%</u>	<u>1%</u> <i>Din 53894</i>
Washing with water	<u>30° C</u>	<u>2%</u>	<u>2%</u> <i>ISO 5077/ISO6330</i>
Drycleaning	<u>P</u>	<u>2%</u>	<u>2%</u> <i>ISO 3175</i>

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours	
Xenotest light	<u>7</u>	<u>7</u>	<u>7</u>	<i>ISO 105-B02</i>
Washing with water	<u>5</u>	<u>4/5</u>	<u>4/5</u>	<i>ISO 105-E01</i>
Drycleaning	<u>5</u>	<u>4/5</u>	<u>4/5</u>	<i>ISO 105-D01</i>
Dry abrasion resistance	<u>5</u>	<u>4/5</u>	<u>4/5</u>	<i>ISO105-X12</i>
Wet abrasion resistance	<u>4/5</u>	<u>4</u>	<u>4</u>	<i>ISO 105-X12</i>

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs 17000		INTENSE USE	<i>ISO 12947-2</i>
Pilling resistance	500 rubs _____	2000 rubs _____	5000 rubs _____	<i>ISO 12945</i>