DEDAR

TECHNICAL PRODUCT SHEET

Article		Collection	Fabric group	CUSTOMS CODE
PON-PON				55143050

FABRIC TYPE

[ ] Fabric for decoration [■] Fabric for upholstery [ ] Fabric for curtains

[ ] [ ] [ ]

TYPE OF MANUFACTURING PROCESS

[ ]	Fibre dyed	[■]	Yarn dyed	[ ]	Piece dyed
[ ]	Cylinder printing	[ ]	Screen printing	[ ]	Digital printing
[ ]	Appliction	[ ]	Corosion	[ ]	Coating
[ ]	Embossing	[ ]	Embroidery	[ ]	Laser

DYES

[ ]	Direct	[ ]	Reactive	[ ]	Acid
[ ]	Pre-metallised	[ ]	Dispersed	[ ]	Others

RECOMMENDED CLEANING INSTRUCTIONS

DESCRIPTIVE FEATURES

Origin of fabric [■] EU [ ] non-EU

Product composition **31%PES 30%WO 24%PAN 13%CO 2%PA** Weave **JACQUARD**

Warp repeat cm ↕ Weft repeat cm ↔

Weight linear mt. **730** Weight sq. metre **515**

Average roll length mt. Minimum roll length mt.

Fabric width with selvedge cm. Fabric width without selvedge cm Useable width cm **140**

DIMENSIONAL STABILITY

		Warp	Weft	
Steam iron	**110° C**	**1%**	**1%**	*Din 53894*
Washing with water				*ISO 5077/ISO6330*
Drycleaning	**P**	**2%**	**2%**	*ISO 3175*

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours	
Xenotest light	**4/5**	**4/5**		*ISO 105-B02*
Washing with water				*ISO 105-E01*
Drycleaning	**4/5**	**4**		*ISO 105-D01*
Dry abrasion resistance	**4/5**	**4**		*ISO105-X12*
Wet abrasion resistance	**4/5**	**3**		*ISO 105-X12*

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa N° rubs **35.000** **INTENSE USE** *ISO 12947-2*

Pilling resistance 500 rubs **4** 2000 rubs **3/4** 5000 rubs **3/4** *ISO 12945*