DEDAR

TECHNICAL PRODUCT SHEET

Article		Collection	Fabric group	CUSTOMS CODE
BELSUEDE				58013600

FABRIC TYPE

[ ] Fabric for decoration	[■] Fabric for upholstery	[ ] Fabric for curtains
[ ]	[ ]	[ ]

TYPE OF MANUFACTURING PROCESS

[ ] Fibre dyed	[■] Yarn dyed	[ ] Piece dyed
[ ] Cylinder printing	[ ] Screen printing	[ ] Digital printing
[ ] Appliction	[ ] Corosion	[ ] Coating
[ ] Embossing	[ ] Embroidery	[ ] Laser

DYES

[ ] Direct	[ ] Reactive	[ ] Acid
[ ] Pre-metallised	[ ] Dispersed	[ ] Others

RECOMMENDED CLEANING INSTRUCTIONS

DESCRIPTIVE FEATURES

Origin of fabric	[■] EU	[ ] non-EU			
Product composition	**55%CV 30%LI 15%CO**			Weave	
Warp repeat cm			Weft repeat cm		
Weight linear mt.	**810**		Weight sq. metre	**565**	
Average roll length mt.			Minimum roll length mt.		
Fabric width with selvedge cm.		Fabric width without selvedge cm		Useable width cm	**140**

DIMENSIONAL STABILITY

		Warp	Weft	
Iron	**110°C**	**1%**	**1%**	*Din 53894*
Washing with water				*ISO 5077/ISO6330*
Drycleaning	**P**	**2%**	**2%**	*ISO 3175*

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours	
Xenotest light	**4/5**	**4/5**	**4/5**	*ISO 105-B02*
Washing with water				*ISO 105-E01*
Drycleaning	**4/5**	**4**	**4**	*ISO 105-D01*
Dry abrasion resistance	**4/5**	**4/5**	**4**	*ISO105-X12*
Wet abrasion resistance	**4**	**3/4**	**3**	*ISO 105-X12*

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa — N° rubs **20.000** — **INTENSE USE** — *ISO 12947-2*

Pilling resistance	500 rubs	2000 rubs	5000 rubs	
	4/5	**4/5**	**4**	*ISO 12945*