

TECHNICAL PRODUCT SHEET

Article MARGARITAS		Collection	Fabric group	CUSTOMS CODE 55169300
------------------------------	--	------------	--------------	--------------------------

FABRIC TYPE

<input checked="" type="checkbox"/> Fabric for decoration	<input type="checkbox"/> Fabric for upholstery	<input type="checkbox"/> Fabric for curtains
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

TYPE OF MANUFACTURING PROCESS

<input type="checkbox"/> Fibre dyed	<input type="checkbox"/> Yarn dyed	<input type="checkbox"/> Piece dyed
<input type="checkbox"/> Cylinder printing	<input checked="" type="checkbox"/> Printing	<input type="checkbox"/> Digital printing
<input type="checkbox"/> Application	<input type="checkbox"/> Corosion	<input type="checkbox"/> Coating
<input type="checkbox"/> Embossing	<input type="checkbox"/> Embroidery	<input type="checkbox"/> Laser
DYES		
<input type="checkbox"/> Direct	<input type="checkbox"/> Reactive	<input type="checkbox"/> Acid
<input type="checkbox"/> Pre-metallised	<input type="checkbox"/> Dispersed	<input type="checkbox"/> Others

RECOMMENDED CLEANING INSTRUCTIONS



DESCRIPTIVE FEATURES

Origin of fabric	<input checked="" type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	70%CV 30%LI	Weave
Warp repeat cm	68	Weft repeat cm
Weight linear mt.	708	Weight sq. metre
Average roll length mt.		Minimum roll length mt.
Fabric width with selvedge cm.		Fabric width without selvedge cm
		Useable width cm
		133

DIMENSIONAL STABILITY

		Warp	Weft	
Steam iron	110° C	1%	1%	<i>Din 53894</i>
Washing with water				<i>ISO 5077/ISO6330</i>
Drycleaning	P	2%	2%	<i>ISO 3175</i>

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours	
Xenotest light	4	4/5		<i>ISO 105-B02</i>
Washing with water				<i>ISO 105-E01</i>
Drycleaning	4/5	4		<i>ISO 105-D01</i>
Dry abrasion resistance	4/5	4		<i>ISO105-X12</i>
Wet abrasion resistance	3/4	3		<i>ISO 105-X12</i>

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs	6.000		LIGHT USE	<i>ISO 12947-2</i>
Pilling resistance	500 rubs	3/4	2000 rubs	3	5000 rubs 3 <i>ISO 12945</i>