

TECHNICAL PRODUCT SHEET

Article MELVILLE		Collection	Fabric group	CUSTOMS CODE 58012100
----------------------------	--	------------	--------------	--------------------------

FABRIC TYPE

<input checked="" type="checkbox"/> Fabric for decoration	<input checked="" type="checkbox"/> Fabric for upholstery	<input checked="" type="checkbox"/> Fabric for curtains
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

TYPE OF MANUFACTURING PROCESS

<input type="checkbox"/> Fibre dyed	<input type="checkbox"/> Yarn dyed	<input checked="" type="checkbox"/> Piece dyed
<input type="checkbox"/> Cylinder printing	<input type="checkbox"/> Screen printing	<input type="checkbox"/> Digital printing
<input type="checkbox"/> Application	<input type="checkbox"/> Corosion	<input type="checkbox"/> Coating
<input type="checkbox"/> Embossing	<input type="checkbox"/> Embroidery	<input type="checkbox"/> Laser
DYES		
<input type="checkbox"/> Direct	<input checked="" type="checkbox"/> Reactive	<input type="checkbox"/> Acid
<input type="checkbox"/> Pre-metallised	<input type="checkbox"/> Dispersed	<input type="checkbox"/> Others

RECOMMENDED CLEANING INSTRUCTIONS



DESCRIPTIVE FEATURES

Origin of fabric	<input checked="" type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	100%CO	Weave _____
Warp repeat cm	_____	Weft repeat cm _____
Weight linear mt.	470	Weight sq. metre 314
Average roll length mt.	_____	Minimum roll length mt. _____
Fabric width with selvedge cm.	_____	Fabric width without selvedge cm _____ Useable width cm 147

DIMENSIONAL STABILITY

	Warp	Weft	
Steam iron	<u>110° C</u>	<u>1%</u>	<u>1%</u> Din 53894
Washing with water	_____	_____	_____ ISO 5077/ISO6330
Drycleaning	<u>P</u>	<u>2%</u>	<u>2%</u> ISO 3175

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours	
Xenotest light	<u>4/5</u>	<u>4/5</u>	<u>3/4</u>	ISO 105-B02
Washing with water	_____	_____	_____	ISO 105-E01
Drycleaning	<u>4/5</u>	<u>4/5</u>	<u>4</u>	ISO 105-D01
Dry abrasion resistance	<u>4/5</u>	<u>4/5</u>	<u>4</u>	ISO105-X12
Wet abrasion resistance	<u>4</u>	<u>3/4</u>	<u>3</u>	ISO 105-X12

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs	30.000		INTENSE USE	ISO 12947-2
Pilling resistance	500 rubs	<u>4/5</u>	2000 rubs	<u>4</u>	5000 rubs <u>3/4</u> ISO 12945