

TECHNICAL PRODUCT SHEET

Article DALIE PAPEVERI TULIPANI	Collection	Fabric group	CUSTOMS CODE 52122490
---	------------	--------------	--------------------------

FABRIC TYPE

<input type="checkbox"/> Fabric for decoration	<input type="checkbox"/> Fabric for upholstery	<input type="checkbox"/> Fabric for curtains
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

TYPE OF MANUFACTURING PROCESS

<input type="checkbox"/> Fibre dyed	<input type="checkbox"/> Yarn dyed	<input type="checkbox"/> Piece dyed
<input type="checkbox"/> Cylinder printing	<input type="checkbox"/> Screen printing	<input type="checkbox"/> Digital printing
<input type="checkbox"/> Application	<input type="checkbox"/> Corosion	<input type="checkbox"/> Coating
<input type="checkbox"/> Embossing	<input type="checkbox"/> Embroidery	<input type="checkbox"/> Laser
DYES		
<input type="checkbox"/> Direct	<input type="checkbox"/> Reactive	<input type="checkbox"/> Acid
<input type="checkbox"/> Pre-metallised	<input type="checkbox"/> Dispersed	<input type="checkbox"/> Others

RECOMMENDED CLEANING INSTRUCTIONS



DESCRIPTIVE FEATURES

Origin of fabric	<input type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	55%CO 19%PES 15%CV 11%SE	
Warp repeat cm	<u>121</u>	Weft repeat cm <u>73,5</u>
Weight linear mt.	<u>388</u>	Weight sq. metre <u>255</u>
Average roll length mt.		Minimum roll length mt.
Fabric width with selvedge cm.	Fabric width without selvedge cm	Useable width cm <u>148</u>

DIMENSIONAL STABILITY

	Warp	Weft	
Steam iron	<u>110° C</u>	<u>1%</u>	<i>Din 53894</i>
Washing with water			<i>ISO 5077/ISO6330</i>
Drycleaning	<u>P</u>	<u>2%</u>	<i>ISO 3175</i>

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours
Xenotest light	<u>4/5</u>	<u>4/5</u>	<i>ISO 105-B02</i>
Washing with water			<i>ISO 105-E01</i>
Drycleaning	<u>4/5</u>	<u>4/5</u>	<i>ISO 105-D01</i>
Dry abrasion resistance			<i>ISO105-X12</i>
Wet abrasion resistance			<i>ISO 105-X12</i>

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs	<i>ISO 12947-2</i>
Pilling resistance	500 rubs _____ 2000 rubs _____ 5000 rubs _____	<i>ISO 12945</i>