

TECHNICAL PRODUCT SHEET

Article <b>KARAKORUM</b>		Collection	Fabric group	CUSTOMS CODE 51129099
-----------------------------	--	------------	--------------	--------------------------

FABRIC TYPE

<input type="checkbox"/> Fabric for decoration	<input type="checkbox"/> Fabric for upholstery	<input type="checkbox"/> Fabric for curtains
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

TYPE OF MANUFACTURING PROCESS

<input type="checkbox"/> Fibre dyed	<input checked="" type="checkbox"/> Yarn dyed	<input type="checkbox"/> Piece dyed
<input type="checkbox"/> Cylinder printing	<input type="checkbox"/> Screen printing	<input type="checkbox"/> Digital printing
<input type="checkbox"/> Application	<input type="checkbox"/> Corosion	<input type="checkbox"/> Coating
<input type="checkbox"/> Embossing	<input type="checkbox"/> Embroidery	<input type="checkbox"/> Laser
DYES		
<input type="checkbox"/> Direct	<input type="checkbox"/> Reactive	<input type="checkbox"/> Acid
<input type="checkbox"/> Pre-metallised	<input type="checkbox"/> Dispersed	<input type="checkbox"/> Others

RECOMMENDED CLEANING INSTRUCTIONS



DESCRIPTIVE FEATURES

Origin of fabric	<input checked="" type="checkbox"/> EU	<input type="checkbox"/> non-EU		
Product composition	Col. 1 42%WO 33%CV 24%CO 1%PA	Col. 2 70%WO 30%CO	Weave	JACQUARD
Warp repeat cm	<input type="text"/>	Weft repeat cm	<input type="text"/>	
Weight linear mt.	Col. 1 1040	Col. 2 905	Weight sq. metre	Col. 1 765 Col. 2 665
Average roll length mt.	<input type="text"/>	Minimum roll length mt.	<input type="text"/>	
Fabric width with selvedge cm.	<input type="text"/>	Fabric width without selvedge cm	Useable width cm	130

DIMENSIONAL STABILITY

		Warp	Weft	
Steam iron	110° C	1%	1%	Din 53894
Washing with water				ISO 5077/ISO6330
Drycleaning	P	2%	2%	ISO 3175

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours
Xenotest light	6	6	ISO 105-B02
Washing with water			ISO 105-E01
Drycleaning	4/5	4	ISO 105-D01
Dry abrasion resistance	4/5	4	ISO105-X12
Wet abrasion resistance	4	3/4	ISO 105-X12

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs	40.000		INTENSE USE	ISO 12947-2
Pilling resistance	500 rubs	2000 rubs	5000 rubs	4/5	ISO 12945