

TECHNICAL PRODUCT SHEET

Article ALTER EGO		Collection	Fabric group	CUSTOMS CODE 54076150
-----------------------------	--	------------	--------------	--------------------------

FABRIC TYPE

<input type="checkbox"/> Fabric for decoration	<input type="checkbox"/> Fabric for upholstery	<input checked="" type="checkbox"/> Fabric for curtains
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

TYPE OF MANUFACTURING PROCESS

<input type="checkbox"/> Fibre dyed	<input checked="" type="checkbox"/> Yarn dyed	<input type="checkbox"/> Piece dyed
<input type="checkbox"/> Cylinder printing	<input type="checkbox"/> Screen printing	<input type="checkbox"/> Digital printing
<input type="checkbox"/> Application	<input type="checkbox"/> Corosion	<input type="checkbox"/> Coating
<input type="checkbox"/> Embossing	<input type="checkbox"/> Embroidery	<input type="checkbox"/> Laser
DYES		
<input type="checkbox"/> Direct	<input type="checkbox"/> Reactive	<input type="checkbox"/> Acid
<input type="checkbox"/> Pre-metallised	<input type="checkbox"/> Dispersed	<input type="checkbox"/> Others

RECOMMENDED CLEANING INSTRUCTIONS



DESCRIPTIVE FEATURES

Origin of fabric	<input checked="" type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	100% PES TREVIRA CS	
Product composition	Weave	
Warp repeat cm	<input type="text"/>	Weft repeat cm
Weight linear mt.	283	Weight sq. metre
		183
Average roll length mt.	<input type="text"/>	Minimum roll length mt.
Fabric width with selvedge cm.	<input type="text"/>	Fabric width without selvedge cm
		Useable width cm
		155

DIMENSIONAL STABILITY

	Warp	Weft	
Steam iron	<u>110° C</u>	<u>1%</u>	<i>Din 53894</i>
Washing with water	<u>30° C</u>	<u>2%</u>	<i>ISO 5077/ISO6330</i>
Drycleaning	<u>P</u>	<u>2%</u>	<i>ISO 3175</i>

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours
Xenotest light	<u>6/7</u>	<u>5</u>	<i>ISO 105-B02</i>
Washing with water	<u>4/5</u>	<u>4</u>	<i>ISO 105-E01</i>
Drycleaning	<u>4/5</u>	<u>4</u>	<i>ISO 105-D01</i>
Dry abrasion resistance	<input type="text"/>	<input type="text"/>	<i>ISO105-X12</i>
Wet abrasion resistance	<input type="text"/>	<input type="text"/>	<i>ISO 105-X12</i>

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs	<i>ISO 12947-2</i>
Pilling resistance	500 rubs <input type="text"/> 2000 rubs <input type="text"/> 5000 rubs <input type="text"/>	<i>ISO 12945</i>

|