

TECHNICAL PRODUCT SHEET				
Article KARANDASH		Collection	Fabric group	CUSTOMS CODE 51129099
FABRIC TYPE				
<input type="checkbox"/>	Fabric for decoration	<input type="checkbox"/>	Fabric for upholstery	<input type="checkbox"/>
()		()		()
TYPE OF MANUFACTURING PROCESS				
()	Fibre dyed	<input checked="" type="checkbox"/>	Yarn dyed	()
()	Cylinder printing	()	Screen printing	()
()	Application	()	Corosion	()
()	Embossing	()	Embroidery	()
DYES				
()	Direct	()	Reactive	()
()	Pre-metallised	()	Dispersed	()
()		()	Acid	()
()		()	Others	()
RECOMMENDED CLEANING INSTRUCTIONS				
DESCRIPTIVE FEATURES				
Origin of fabric	<input checked="" type="checkbox"/>	EU	()	non-EU
Product composition	70%WO 30%CO			Weave JACQUARD
Warp repeat cm	↕		Weft repeat cm	↔
Weight linear mt.		885	Weight sq. metre	665
Average roll length mt.			Minimum roll length mt.	
Fabric width with selvedge cm.			Fabric width without selvedge cm	
			Useable width cm	130
DIMENSIONAL STABILITY				
		Warp	Weft	
Steam iron	<u>110° C</u>	<u>1%</u>	<u>1%</u>	<i>Din 53894</i>
Washing with water	<u> </u>	<u> </u>	<u> </u>	<i>ISO 5077/ISO6330</i>
Drycleaning	<u>P</u>	<u>2%</u>	<u>2%</u>	<i>ISO 3175</i>
COLOUR FASTNESS				
	<u>Light colours</u>	<u>Dark colours</u>	<u>Pastel colours</u>	
Xenotest light	<u>5</u>	<u>6</u>	<u> </u> <i>ISO 105-B02</i>	
Washing with water	<u> </u>	<u> </u>	<u> </u> <i>ISO 105-E01</i>	
Drycleaning	<u>4/5</u>	<u>4</u>	<u> </u> <i>ISO 105-D01</i>	
Dry abrasion resistance	<u>4/5</u>	<u>4</u>	<u> </u> <i>ISO105-X12</i>	
Wet abrasion resistance	<u>4</u>	<u>3/4</u>	<u> </u> <i>ISO 105-X12</i>	
MECHANICAL CHARACTERISTICS				
Resistance to Martindale test 12k/Pa	N° rubs	40.000		INTENSE USE <i>ISO 12947-2</i>
Pilling resistance	500 rubs	2000 rubs	5000 rubs	<u>4/5</u> <i>ISO 12945</i>