

TECHNICAL PRODUCT SHEET

Article <b>ARALDO</b>		Collection	Fabric group	CUSTOMS CODE 54076150
--------------------------	--	------------	--------------	--------------------------

FABRIC TYPE

<input type="checkbox"/> Fabric for decoration	<input type="checkbox"/> Fabric for upholstery	<input type="checkbox"/> Fabric for curtains
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

TYPE OF MANUFACTURING PROCESS

<input type="checkbox"/> Fibre dyed	<input checked="" type="checkbox"/> Yarn dyed	<input type="checkbox"/> Piece dyed
<input type="checkbox"/> Cylinder printing	<input type="checkbox"/> Screen printing	<input type="checkbox"/> Digital printing
<input type="checkbox"/> Application	<input type="checkbox"/> Corosion	<input type="checkbox"/> Coating
<input type="checkbox"/> Embossing	<input type="checkbox"/> Embroidery	<input type="checkbox"/> Laser
DYES		
<input type="checkbox"/> Direct	<input type="checkbox"/> Reactive	<input type="checkbox"/> Acid
<input type="checkbox"/> Pre-metallised	<input type="checkbox"/> Dispersed	<input type="checkbox"/> Others

RECOMMENDED CLEANING INSTRUCTIONS



DESCRIPTIVE FEATURES

Origin of fabric	<input checked="" type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	<b>100%PES TREVIRA CS</b>	Weave <b>JACQUARD</b>
Warp repeat cm	<b>2,5</b>	Weft repeat cm <b>2,5</b>
Weight linear mt.	<b>302</b>	Weight sq. metre <b>213</b>
Average roll length mt.		Minimum roll length mt.
Fabric width with selvedge cm.		Fabric width without selvedge cm
		Useable width cm <b>140</b>

DIMENSIONAL STABILITY

	Warp	Weft	
Steam iron	<b>110° C</b>	<b>1%</b>	<i>Din 53894</i>
Washing with water	<b>30° C</b>	<b>2%</b>	<i>ISO 5077/ISO6330</i>
Drycleaning	<b>P</b>	<b>2%</b>	<i>ISO 3175</i>

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours
Xenotest light	<b>4/5</b>	<b>4</b>	<i>ISO 105-B02</i>
Washing with water	<b>4/5</b>	<b>4/5</b>	<i>ISO 105-E01</i>
Drycleaning	<b>4/5</b>	<b>4/5</b>	<i>ISO 105-D01</i>
Dry abrasion resistance	<b>4/5</b>	<b>4/5</b>	<i>ISO105-X12</i>
Wet abrasion resistance	<b>4/5</b>	<b>4/5</b>	<i>ISO 105-X12</i>

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs <b>6.000</b>		<b>LIGHT USE</b>	<i>ISO 12947-2</i>
Pilling resistance	500 rubs	2000 rubs	5000 rubs	<b>5</b> <i>ISO 12945</i>