DEDAR

TECHNICAL PRODUCT SHEET

Article		Collection	Fabric group	CUSTOMS CODE
DRAGUEUR				54075300

FABRIC TYPE

■ Fabric for decoration	■ Fabric for upholstery	■ Fabric for curtains
[ ]	[ ]	[ ]

TYPE OF MANUFACTURING PROCESS

[ ] Fibre dyed	■ Yarn dyed	[ ] Piece dyed
[ ] Cylinder printing	[ ] Screen printing	[ ] Digital printing
[ ] Appliction	[ ] Corosion	[ ] Coating
[ ] Embossing	[ ] Embroidery	[ ] Laser

DYES

[ ] Direct	[ ] Reactive	[ ] Acid
[ ] Pre-metallised	[ ] Dispersed	[ ] Others

RECOMMENDED CLEANING INSTRUCTIONS

DESCRIPTIVE FEATURES

Origin of fabric: ■ EU [ ] non-EU

Product composition	**100%PES TREVIRA CS**			Weave	**JACQUARD**
Warp repeat cm	**5,5**		Weft repeat cm		**3,5**
Weight linear mt.	**208**		Weight sq. metre		**147**
Average roll length mt.			Minimum roll length mt.		
Fabric width with selvedge cm.		Fabric width without selvedge cm		Useable width cm	**140**

DIMENSIONAL STABILITY

		Warp	Weft	
Steam iron	**110° C**	**1%**	**1%**	*Din 53894*
Washing with water	**30°C**	**2%**	**2%**	*ISO 5077/ISO6330*
Drycleaning	**P**	**2%**	**2%**	*ISO 3175*

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours	
Xenotest light	**4/5**	**3/4**		*ISO 105-B02*
Washing with water	**4/5**	**4/5**		*ISO 105-E01*
Drycleaning	**4/5**	**4/5**		*ISO 105-D01*
Dry abrasion resistance	**4/5**	**4/5**		*ISO105-X12*
Wet abrasion resistance	**4/5**	**4/5**		*ISO 105-X12*

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs	**5.000**		**LIGHT USE**	*ISO 12947-2*
Pilling resistance	500 rubs		2000 rubs	5000 rubs	**4/5** *ISO 12945*