DEDAR

# TECHNICAL PRODUCT SHEET

| Article | | Collection | Fabric group | CUSTOMS CODE |
|---|---|---|---|---|
| **MICROGRAMMA** | | | | 54075300 |

## FABRIC TYPE

| | | |
|---|---|---|
| ■ Fabric for decoration | ■ Fabric for upholstery | ■ Fabric for curtains |
| [ ] | [ ] | [ ] |

## TYPE OF MANUFACTURING PROCESS

| | | |
|---|---|---|
| [ ] Fibre dyed | ■ Yarn dyed | [ ] Piece dyed |
| [ ] Cylinder printing | [ ] Screen printing | [ ] Digital printing |
| [ ] Appliction | [ ] Corosion | [ ] Coating |
| [ ] Embossing | [ ] Embroidery | [ ] Laser |

### DYES

| | | |
|---|---|---|
| [ ] Direct | [ ] Reactive | [ ] Acid |
| [ ] Pre-metallised | [ ] Dispersed | [ ] Others |

## RECOMMENDED CLEANING INSTRUCTIONS

## DESCRIPTIVE FEATURES

Origin of fabric ■ EU [ ] non-EU

| | | | |
|---|---|---|---|
| Product composition | **100%PES TREVIRA CS** | Weave | **JACQUARD** |
| Warp repeat cm | | Weft repeat cm | |
| Weight linear mt. | **220** | Weight sq. metre | **156** |
| Average roll length mt. | | Minimum roll length mt. | |
| Fabric width with selvedge cm. | | Fabric width without selvedge cm | Useable width cm **140** |

## DIMENSIONAL STABILITY

| | | Warp | Weft | |
|---|---|---|---|---|
| Steam iron | **110° C** | **1%** | **1%** | *Din 53894* |
| Washing with water | **30°C** | **2%** | **2%** | *ISO 5077/ISO6330* |
| Drycleaning | **P** | **2%** | **2%** | *ISO 3175* |

## COLOUR FASTNESS

| | Light colours | Dark colours | Pastel colours | |
|---|---|---|---|---|
| Xenotest light | **3/4** | **5** | | *ISO 105-B02* |
| Washing with water | **4/5** | **4/5** | | *ISO 105-E01* |
| Drycleaning | **4/5** | **4/5** | | *ISO 105-D01* |
| Dry abrasion resistance | **4/5** | **4/5** | | *ISO105-X12* |
| Wet abrasion resistance | **4/5** | **4/5** | | *ISO 105-X12* |

## MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa — N° rubs **12.000** — **NORMAL USE** — *ISO 12947-2*

Pilling resistance — 500 rubs — 2000 rubs — 5000 rubs **5** — *ISO 12945*