DEDAR

TECHNICAL PRODUCT SHEET

Article		Collection	Fabric group	CUSTOMS CODE
REGIMEN				54075300

FABRIC TYPE

■ Fabric for decoration	■ Fabric for upholstery	■ Fabric for curtains
[ ]	[ ]	[ ]

TYPE OF MANUFACTURING PROCESS

[ ] Fibre dyed	■ Yarn dyed	[ ] Piece dyed
[ ] Cylinder printing	[ ] Screen printing	[ ] Digital printing
[ ] Appliction	[ ] Corosion	[ ] Coating
[ ] Embossing	[ ] Embroidery	[ ] Laser

DYES

[ ] Direct	[ ] Reactive	[ ] Acid
[ ] Pre-metallised	[ ] Dispersed	[ ] Others

RECOMMENDED CLEANING INSTRUCTIONS

DESCRIPTIVE FEATURES

Origin of fabric ■ EU [ ] non-EU

Product composition	**100%PES TREVIRA CS**			Weave	**JACQUARD**
Warp repeat cm			Weft repeat cm		**4,5**
Weight linear mt.	**456**		Weight sq. metre		**145**
Average roll length mt.			Minimum roll length mt.		
Fabric width with selvedge cm.		Fabric width without selvedge cm		Useable width cm	**315**

DIMENSIONAL STABILITY

		Warp	Weft	
Steam iron	**110° C**	**1%**	**1%**	*Din 53894*
Washing with water	**30°C**	**2%**	**2%**	*ISO 5077/ISO6330*
Drycleaning	**P**	**2%**	**2%**	*ISO 3175*

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours	
Xenotest light	**4**	**4**		*ISO 105-B02*
Washing with water	**4/5**	**4/5**		*ISO 105-E01*
Drycleaning	**4/5**	**4/5**		*ISO 105-D01*
Dry abrasion resistance	**4/5**	**4/5**		*ISO105-X12*
Wet abrasion resistance	**4/5**	**4/5**		*ISO 105-X12*

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa — N° rubs **10.000** — **NORMAL USE** — *ISO 12947-2*

Pilling resistance	500 rubs		2000 rubs		5000 rubs	**5** *ISO 12945*