

TECHNICAL PRODUCT SHEET

Article SCHWARZWALD		Collection	Fabric group	CUSTOMS CODE
-------------------------------	--	------------	--------------	--------------

FABRIC TYPE

<input type="checkbox"/> Fabric for decoration	<input type="checkbox"/> Fabric for upholstery	<input type="checkbox"/> Fabric for curtains
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

TYPE OF MANUFACTURING PROCESS

<input type="checkbox"/> Fibre dyed	<input type="checkbox"/> Yarn dyed	<input type="checkbox"/> Piece dyed
<input type="checkbox"/> Cylinder printing	<input type="checkbox"/> Screen printing	<input checked="" type="checkbox"/> Printing
<input type="checkbox"/> Application	<input type="checkbox"/> Corosion	<input type="checkbox"/> Coating
<input type="checkbox"/> Embossing	<input type="checkbox"/> Embroidery	<input type="checkbox"/> Laser
DYES		
<input type="checkbox"/> Direct	<input type="checkbox"/> Reactive	<input type="checkbox"/> Acid
<input type="checkbox"/> Pre-metallised	<input type="checkbox"/> Dispersed	<input type="checkbox"/> Others

RECOMMENDED CLEANING INSTRUCTIONS



WR

DESCRIPTIVE FEATURES

Origin of fabric	<input checked="" type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	60%CV 16%LI 13%CO 6%PES 5%PAN	
Warp repeat cm	88	Weft repeat cm 138
Weight linear mt.	644	Weight sq. metre 457
Average roll length mt.		Minimum roll length mt.
Fabric width with selvedge cm.		Fabric width without selvedge cm
		Useable width cm 140

DIMENSIONAL STABILITY

		Warp	Weft	
Steam iron	110° C	1%	1%	<i>Din 53894</i>
Washing with water				<i>ISO 5077/ISO6330</i>
Drycleaning	P	2%	2%	<i>ISO 3175</i>

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours
Xenotest light	5	4/5	<i>ISO 105-B02</i>
Washing with water			<i>ISO 105-E01</i>
Drycleaning	4	4	<i>ISO 105-D01</i>
Dry abrasion resistance	4/5	4/5	<i>ISO105-X12</i>
Wet abrasion resistance	3	3	<i>ISO 105-X12</i>

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs	15.000		INTENSE USE	<i>ISO 12947-2</i>
Pilling resistance	500 rubs	2000 rubs	5000 rubs	3	<i>ISO 12945</i>