

TECHNICAL PRODUCT SHEET

Article T19006 TADZIO	Collection	Fabric group	CUSTOMS CODE 53091900
---------------------------------	------------	--------------	--------------------------

FABRIC TYPE

- | | | |
|------------------------------------------------|------------------------------------------------|---------------------------------------------------------|
| <input type="checkbox"/> Fabric for decoration | <input type="checkbox"/> Fabric for upholstery | <input checked="" type="checkbox"/> Fabric for curtains |
| <input type="checkbox"/> | <input type="checkbox"/> | <input type="checkbox"/> |

TYPE OF MANUFACTURING PROCESS

- | | | |
|--------------------------------------------|-----------------------------------------------|-------------------------------------------|
| <input type="checkbox"/> Fibre dyed | <input checked="" type="checkbox"/> Yarn dyed | <input type="checkbox"/> Piece dyed |
| <input type="checkbox"/> Cylinder printing | <input type="checkbox"/> Screen printing | <input type="checkbox"/> Digital printing |
| <input type="checkbox"/> Application | <input type="checkbox"/> Corosion | <input type="checkbox"/> Coating |
| <input type="checkbox"/> Embossing | <input type="checkbox"/> Embroidery | <input type="checkbox"/> Laser |
- DYES**
- | | | |
|-----------------------------------------|------------------------------------|---------------------------------|
| <input type="checkbox"/> Direct | <input type="checkbox"/> Reactive | <input type="checkbox"/> Acid |
| <input type="checkbox"/> Pre-metallised | <input type="checkbox"/> Dispersed | <input type="checkbox"/> Others |

RECOMMENDED CLEANING INSTRUCTIONS



DESCRIPTIVE FEATURES

Origin of fabric	<input checked="" type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	100%LI	Weave _____
Warp repeat cm	↕ _____	Weft repeat cm
Weight linear mt.	900	Weight sq. metre 285
Average roll length mt.	_____	Minimum roll length mt.
Fabric width with selvedge cm.	_____	Fabric width without selvedge cm _____ Useable width cm 310

DIMENSIONAL STABILITY

	Warp	Weft	
Steam iron	<u>110° C</u>	<u>1%</u>	<i>Din 53894</i>
Washing with water	<u>30°C</u>	<u>2%</u>	<i>ISO 5077/ISO6330</i>
Drycleaning	<u>P</u>	<u>2%</u>	<i>ISO 3175</i>

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours
Xenotest light	<u>6</u>	<u>6/7</u>	<i>ISO 105-B02</i>
Washing with water	<u>4/5</u>	<u>4/5</u>	<i>ISO 105-E01</i>
Drycleaning	<u>4/5</u>	<u>4/5</u>	<i>ISO 105-D01</i>
Dry abrasion resistance	_____	_____	<i>ISO105-X12</i>
Wet abrasion resistance	_____	_____	<i>ISO 105-X12</i>

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs	<i>ISO 12947-2</i>
Pilling resistance	500 rubs _____ 2000 rubs _____ 5000 rubs _____	<i>ISO 12945</i>