

TECHNICAL PRODUCT SHEET

Article T19036 YOUNG AND LOVELY	Collection	Fabric group	CUSTOMS CODE 54079300
---	------------	--------------	--------------------------

FABRIC TYPE

<input type="checkbox"/> Fabric for decoration	<input type="checkbox"/> Fabric for upholstery	<input type="checkbox"/> Fabric for curtains
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

TYPE OF MANUFACTURING PROCESS

<input type="checkbox"/> Fibre dyed	<input type="checkbox"/> Yarn dyed	<input type="checkbox"/> Solution dyed
<input type="checkbox"/> Cylinder printing	<input type="checkbox"/> Screen printing	<input type="checkbox"/> Digital printing
<input type="checkbox"/> Application	<input type="checkbox"/> Corosion	<input type="checkbox"/> Coating
<input type="checkbox"/> Embossing	<input type="checkbox"/> Embroidery	<input type="checkbox"/> Laser
DYES		
<input type="checkbox"/> Direct	<input type="checkbox"/> Reactive	<input type="checkbox"/> Acid
<input type="checkbox"/> Pre-metallised	<input type="checkbox"/> Dispersed	<input type="checkbox"/> Others

RECOMMENDED CLEANING INSTRUCTIONS



DESCRIPTIVE FEATURES

Origin of fabric	<input type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	100%PP	Weave _____
Warp repeat cm	12	Weft repeat cm _____
Weight linear mt.	400	Weight sq. metre 286
Average roll length mt.	_____	Minimum roll length mt. _____
Fabric width with selvedge cm.	_____	Fabric width without selvedge cm _____ Useable width cm 140

DIMENSIONAL STABILITY

	Warp	Weft	
Steam iron	110° C	1%	<i>Din 53894</i>
Washing with water	30° C	2%	<i>ISO 5077/ISO6330</i>
Drycleaning	_____	_____	<i>ISO 3175</i>

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours
Xenotest light	6	6/7	<i>ISO 105-B02</i>
Washing with water	4/5	4/5	<i>ISO 105-E01</i>
Drycleaning	_____	_____	<i>ISO 105-D01</i>
Dry abrasion resistance	4/5	4/5	<i>ISO105-X12</i>
Wet abrasion resistance	4/5	4	<i>ISO 105-X12</i>

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs 22.000		INTENSE USE	<i>ISO 12947-2</i>
Pilling resistance	500 rubs _____	2000 rubs _____	5000 rubs 4/5	<i>ISO 12945</i>