

TECHNICAL PRODUCT SHEET

Article T19046 FARNIENTE	Collection	Fabric group	CUSTOMS CODE 55122990
------------------------------------	------------	--------------	--------------------------

FABRIC TYPE

<input checked="" type="checkbox"/> Fabric for decoration	<input checked="" type="checkbox"/> Fabric for upholstery	<input type="checkbox"/> Fabric for curtains
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

TYPE OF MANUFACTURING PROCESS

<input checked="" type="checkbox"/> Fibre dyed	<input type="checkbox"/> Yarn dyed	<input type="checkbox"/> Solution dyed
<input type="checkbox"/> Cylinder printing	<input type="checkbox"/> Screen printing	<input type="checkbox"/> Digital printing
<input type="checkbox"/> Appliption	<input type="checkbox"/> Corosion	<input type="checkbox"/> Coating
<input type="checkbox"/> Embossing	<input type="checkbox"/> Embroidery	<input type="checkbox"/> Laser
DYES		
<input type="checkbox"/> Direct	<input type="checkbox"/> Reactive	<input type="checkbox"/> Acid
<input type="checkbox"/> Pre-metallised	<input type="checkbox"/> Dispersed	<input type="checkbox"/> Others

RECOMMENDED CLEANING INSTRUCTIONS



DOUBLE FACE

DESCRIPTIVE FEATURES

Origin of fabric	<input checked="" type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	100%PAN	Weave _____
Warp repeat cm	↕ _____	Weft repeat cm ← _____
Weight linear mt.	500	Weight sq. metre 360
Average roll length mt.	_____	Minimum roll length mt. _____
Fabric width with selvedge cm.	_____	Fabric width without selvedge cm _____ Useable width cm 140

DIMENSIONAL STABILITY

	Warp	Weft	
Steam iron	<u>110° C</u>	<u>1%</u>	<u>1%</u> <i>Din 53894</i>
Washing with water	<u>30° C</u>	<u>2%</u>	<u>2%</u> <i>ISO 5077/ISO6330</i>
Drycleaning	<u>P</u>	<u>2%</u>	<u>2%</u> <i>ISO 3175</i>

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours
Xenotest light	<u>6</u>	<u>6/7</u>	_____ <i>ISO 105-B02</i>
Washing with water	<u>4/5</u>	<u>4/5</u>	_____ <i>ISO 105-E01</i>
Drycleaning	<u>4/5</u>	<u>4/5</u>	_____ <i>ISO 105-D01</i>
Dry abrasion resistance	<u>4/5</u>	<u>4/5</u>	_____ <i>ISO105-X12</i>
Wet abrasion resistance	<u>4/5</u>	<u>4</u>	_____ <i>ISO 105-X12</i>

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs 23.000		INTENSE USE	<i>ISO 12947-2</i>
Pilling resistance	500 rubs _____	2000 rubs _____	5000 rubs 3/4	<i>ISO 12945</i>