

TECHNICAL PRODUCT SHEET

Article T20001 SUNDAY	Collection	Fabric group	CUSTOMS CODE 58013700
---------------------------------	------------	--------------	--------------------------

FABRIC TYPE

<input type="checkbox"/> Fabric for decoration	<input type="checkbox"/> Fabric for upholstery	<input type="checkbox"/> Fabric for curtains
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

TYPE OF MANUFACTURING PROCESS

<input type="checkbox"/> Fibre dyed	<input type="checkbox"/> Yarn dyed	<input checked="" type="checkbox"/> Piece dyed
<input type="checkbox"/> Cylinder printing	<input type="checkbox"/> Screen printing	<input type="checkbox"/> Digital printing
<input type="checkbox"/> Application	<input type="checkbox"/> Corosion	<input type="checkbox"/> Coating
<input type="checkbox"/> Embossing	<input type="checkbox"/> Embroidery	<input type="checkbox"/> Laser
DYES		
<input type="checkbox"/> Direct	<input type="checkbox"/> Reactive	<input type="checkbox"/> Acid
<input type="checkbox"/> Pre-metallised	<input type="checkbox"/> Dispersed	<input type="checkbox"/> Others

RECOMMENDED CLEANING INSTRUCTIONS



DESCRIPTIVE FEATURES

Origin of fabric	<input checked="" type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	100%PES TREVIRA CS	Weave _____
Warp repeat cm	↕ _____	Weft repeat cm
Weight linear mt.	553	Weight sq. metre
Average roll length mt.	_____	Minimum roll length mt.
Fabric width with selvedge cm.	_____	Fabric width without selvedge cm
		Useable width cm
		140

DIMENSIONAL STABILITY

	Warp	Weft	
Steam iron	<u>110° C</u>	<u>1%</u>	<u>Din 53894</u>
Washing with water	<u>30°C</u>	<u>2%</u>	<u>ISO 5077/ISO6330</u>
Drycleaning	<u>P</u>	<u>2%</u>	<u>ISO 3175</u>

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours
Xenotest light	<u>5/6</u>	<u>> 6</u>	<u>ISO 105-B02</u>
Washing with water	<u>4/5</u>	<u>4/5</u>	<u>ISO 105-E01</u>
Drycleaning	<u>4/5</u>	<u>4/5</u>	<u>ISO 105-D01</u>
Dry abrasion resistance	<u>4/5</u>	<u>4/5</u>	<u>ISO105-X12</u>
Wet abrasion resistance	<u>4/5</u>	<u>3/4</u>	<u>ISO 105-X12</u>

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs	100.000		INTENSE USE	<u>ISO 12947-2</u>
Pilling resistance	500 rubs	_____	2000 rubs	_____	5000 rubs
				5	<u>ISO 12945</u>