

TECHNICAL PRODUCT SHEET

Article T20005 CORIANDOLI	Collection	Fabric group	CUSTOMS CODE 54079300
-------------------------------------	------------	--------------	--------------------------

FABRIC TYPE

<input type="checkbox"/> Fabric for decoration	<input type="checkbox"/> Fabric for upholstery	<input type="checkbox"/> Fabric for curtains
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

TYPE OF MANUFACTURING PROCESS

<input type="checkbox"/> Fibre dyed	<input checked="" type="checkbox"/> Yarn dyed	<input type="checkbox"/> Piece dyed
<input type="checkbox"/> Cylinder printing	<input type="checkbox"/> Screen printing	<input type="checkbox"/> Digital printing
<input type="checkbox"/> Application	<input type="checkbox"/> Corosion	<input type="checkbox"/> Coating
<input type="checkbox"/> Embossing	<input type="checkbox"/> Embroidery	<input type="checkbox"/> Laser
DYES		
<input type="checkbox"/> Direct	<input type="checkbox"/> Reactive	<input type="checkbox"/> Acid
<input type="checkbox"/> Pre-metallised	<input type="checkbox"/> Dispersed	<input type="checkbox"/> Others

RECOMMENDED CLEANING INSTRUCTIONS



DESCRIPTIVE FEATURES

Origin of fabric	<input checked="" type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	64%PES 32%PA 4%PM	
Warp repeat cm	3	Weft repeat cm 3,5
Weight linear mt.	690	Weight sq. metre 490
Average roll length mt.		Minimum roll length mt.
Fabric width with selvedge cm.		Fabric width without selvedge cm
		Useable width cm 140

DIMENSIONAL STABILITY

	Warp	Weft	
Steam iron	<u>110° C</u>	<u>1%</u>	<i>Din 53894</i>
Washing with water	<u>30°C</u>	<u>2%</u>	<i>ISO 5077/ISO6330</i>
Drycleaning	<u>P</u>	<u>2%</u>	<i>ISO 3175</i>

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours
Xenotest light	<u>5/6</u>	<u>5</u>	<i>ISO 105-B02</i>
Washing with water	<u>4/5</u>	<u>4/5</u>	<i>ISO 105-E01</i>
Drycleaning	<u>4/5</u>	<u>4/5</u>	<i>ISO 105-D01</i>
Dry abrasion resistance	<u>4/5</u>	<u>4/5</u>	<i>ISO105-X12</i>
Wet abrasion resistance	<u>4/5</u>	<u>3/4</u>	<i>ISO 105-X12</i>

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs 23.300		INTENSE USE	<i>ISO 12947-2</i>
Pilling resistance	500 rubs	2000 rubs	5000 rubs	5 <i>ISO 12945</i>