

TECHNICAL PRODUCT SHEET

Article <b>T20015 ATELIER MODERNE</b>	Collection	Fabric group	CUSTOMS CODE 53091900
--	------------	--------------	--------------------------

FABRIC TYPE

<input type="checkbox"/> Fabric for decoration	<input checked="" type="checkbox"/> Fabric for upholstery	<input type="checkbox"/> Fabric for curtains
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

TYPE OF MANUFACTURING PROCESS

<input type="checkbox"/> Fibre dyed	<input checked="" type="checkbox"/> Yarn dyed	<input type="checkbox"/> Piece dyed
<input type="checkbox"/> Cylinder printing	<input type="checkbox"/> Screen printing	<input type="checkbox"/> Digital printing
<input type="checkbox"/> Application	<input type="checkbox"/> Corosion	<input type="checkbox"/> Coating
<input type="checkbox"/> Embossing	<input type="checkbox"/> Embroidery	<input type="checkbox"/> Laser
<b>DYES</b>		
<input type="checkbox"/> Direct	<input type="checkbox"/> Reactive	<input type="checkbox"/> Acid
<input type="checkbox"/> Pre-metallised	<input type="checkbox"/> Dispersed	<input type="checkbox"/> Others

RECOMMENDED CLEANING INSTRUCTIONS



DESCRIPTIVE FEATURES

Origin of fabric	<input checked="" type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	<b>92%LI 8%PA</b>	Weave _____
Warp repeat cm	↕ _____	Weft repeat cm
Weight linear mt.	<b>1.015</b>	Weight sq. metre
Average roll length mt.	_____	Minimum roll length mt.
Fabric width with selvedge cm.	_____	Fabric width without selvedge cm
		Useable width cm
		<b>143</b>

DIMENSIONAL STABILITY

	Warp	Weft	
Steam iron	<b>110° C</b>	<b>1%</b>	<i>Din 53894</i>
Washing with water	_____	_____	<i>ISO 5077/ISO6330</i>
Drycleaning	<b>P</b>	<b>2%</b>	<i>ISO 3175</i>

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours
Xenotest light	<b>4/5</b>	<b>5</b>	_____ <i>ISO 105-B02</i>
Washing with water	_____	_____	_____ <i>ISO 105-E01</i>
Drycleaning	<b>4/5</b>	<b>4/5</b>	_____ <i>ISO 105-D01</i>
Dry abrasion resistance	<b>4/5</b>	<b>4/5</b>	_____ <i>ISO105-X12</i>
Wet abrasion resistance	<b>4/5</b>	<b>3/4</b>	_____ <i>ISO 105-X12</i>

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs	<b>&gt; 40.000</b>		<b>INTENSE USE</b>	<i>ISO 12947-2</i>
Pilling resistance	500 rubs	_____	2000 rubs	_____	5000 rubs
				<b>3</b>	<i>ISO 12945</i>