

TECHNICAL PRODUCT SHEET

Article T20018 FANDANGO	Collection	Fabric group	CUSTOMS CODE 54078300
-----------------------------------	------------	--------------	--------------------------

FABRIC TYPE

<input type="checkbox"/> Fabric for decoration	<input checked="" type="checkbox"/> Fabric for upholstery	<input type="checkbox"/> Fabric for curtains
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

TYPE OF MANUFACTURING PROCESS

<input type="checkbox"/> Fibre dyed	<input checked="" type="checkbox"/> Yarn dyed	<input type="checkbox"/> Piece dyed
<input type="checkbox"/> Cylinder printing	<input type="checkbox"/> Screen printing	<input type="checkbox"/> Digital printing
<input type="checkbox"/> Application	<input type="checkbox"/> Corosion	<input type="checkbox"/> Coating
<input type="checkbox"/> Embossing	<input type="checkbox"/> Embroidery	<input type="checkbox"/> Laser
DYES		
<input type="checkbox"/> Direct	<input type="checkbox"/> Reactive	<input type="checkbox"/> Acid
<input type="checkbox"/> Pre-metallised	<input type="checkbox"/> Dispersed	<input type="checkbox"/> Others

RECOMMENDED CLEANING INSTRUCTIONS



DESCRIPTIVE FEATURES

Origin of fabric	<input checked="" type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	78%PES 22%CO	
Warp repeat cm	21	Weft repeat cm 145
Weight linear mt.	377	Weight sq. metre 255
Average roll length mt.		Minimum roll length mt.
Fabric width with selvedge cm.		Fabric width without selvedge cm
		Useable width cm 145

DIMENSIONAL STABILITY

	Warp	Weft	
Steam iron	110° C	1%	<i>Din 53894</i>
Washing with water			<i>ISO 5077/ISO6330</i>
Drycleaning	P	2%	<i>ISO 3175</i>

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours
Xenotest light	5/6	4/5	<i>ISO 105-B02</i>
Washing with water			<i>ISO 105-E01</i>
Drycleaning	4/5	4/5	<i>ISO 105-D01</i>
Dry abrasion resistance	4/5	4/5	<i>ISO105-X12</i>
Wet abrasion resistance	4/5	4/5	<i>ISO 105-X12</i>

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs 10.000		NORMAL USE	<i>ISO 12947-2</i>
Pilling resistance	500 rubs	2000 rubs	5000 rubs	3 <i>ISO 12945</i>