

TECHNICAL PRODUCT SHEET

Article <b>TABULARASA</b>		Collection	Fabric group	CUSTOMS CODE 52093900
------------------------------	--	------------	--------------	--------------------------

FABRIC TYPE

<input type="checkbox"/>	Fabric for decoration	<input checked="" type="checkbox"/>	Fabric for upholstery	<input type="checkbox"/>	Fabric for curtains
<input type="checkbox"/>		<input type="checkbox"/>		<input type="checkbox"/>	

TYPE OF MANUFACTURING PROCESS

<input type="checkbox"/>	Fibre dyed	<input type="checkbox"/>	Yarn dyed	<input checked="" type="checkbox"/>	Piece dyed
<input type="checkbox"/>	Cylinder printing	<input type="checkbox"/>	Screen printing	<input type="checkbox"/>	Digital printing
<input type="checkbox"/>	Application	<input type="checkbox"/>	Corosion	<input type="checkbox"/>	Coating
<input type="checkbox"/>	Embossing	<input type="checkbox"/>	Embroidery	<input type="checkbox"/>	Laser
<b>DYES</b>					
<input type="checkbox"/>	Direct	<input checked="" type="checkbox"/>	Reactive	<input type="checkbox"/>	Acid
<input type="checkbox"/>	Pre-metallised	<input type="checkbox"/>	Dispersed	<input type="checkbox"/>	Others

RECOMMENDED CLEANING INSTRUCTIONS



DESCRIPTIVE FEATURES

Origin of fabric	<input checked="" type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	<b>100% CO</b>	Weave <b>SATIN</b>
Warp repeat cm		Weft repeat cm
Weight linear mt.	<b>469</b>	Weight sq. metre <b>335</b>
Average roll length mt.		Minimum roll length mt.
Fabric width with selvedge cm.	<b>142</b>	Fabric width without selvedge cm
		Useable width cm <b>140</b>

DIMENSIONAL STABILITY

	Warp	Weft	
Steam iron	<b>110°C</b>	<b>1%</b>	<i>Din 53894</i>
Washing with water			<i>ISO 5077/ISO6330</i>
Drycleaning	<b>P</b>	<b>2%</b>	<i>ISO 3175</i>

COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours	
Xenotest light	<b>4/5</b>	<b>4/5</b>	<b>3/4</b>	<i>ISO 105-B02</i>
Washing with water				<i>ISO 105-E01</i>
Drycleaning	<b>5</b>	<b>4/5</b>	<b>4/5</b>	<i>ISO 105-D01</i>
Dry abrasion resistance	<b>5</b>	<b>4/5</b>	<b>4/5</b>	<i>ISO105-X12</i>
Wet abrasion resistance	<b>4/5</b>	<b>4</b>	<b>3/4</b>	<i>ISO 105-X12</i>

MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs <b>30000</b>		<b>INTENSE USE</b>	<i>ISO 12947-2</i>
Pilling resistance	500 rubs <b>4/5</b>	2000 rubs <b>4/5</b>	5000 rubs <b>4/5</b>	<i>ISO 12945</i>