

## TECHNICAL PRODUCT SHEET

Article <b>TUXEDO</b>		Collection	Fabric group	CUSTOMS CODE 54077300
--------------------------	--	------------	--------------	--------------------------

### FABRIC TYPE

<input type="checkbox"/> Fabric for decoration	<input type="checkbox"/> Fabric for upholstery	<input type="checkbox"/> Fabric for curtains
<input type="checkbox"/>	<input type="checkbox"/>	<input type="checkbox"/>

### TYPE OF MANUFACTURING PROCESS

<input type="checkbox"/> Fibre dyed	<input type="checkbox"/> Yarn dyed	<input type="checkbox"/> Piece dyed
<input type="checkbox"/> Cylinder printing	<input type="checkbox"/> Screen printing	<input type="checkbox"/> Digital printing
<input type="checkbox"/> Application	<input type="checkbox"/> Corosion	<input type="checkbox"/> Coating
<input type="checkbox"/> Embossing	<input type="checkbox"/> Embroidery	<input type="checkbox"/> Laser
<b>DYES</b>		
<input type="checkbox"/> Direct	<input type="checkbox"/> Reactive	<input type="checkbox"/> Acid
<input type="checkbox"/> Pre-metallised	<input type="checkbox"/> Dispersed	<input type="checkbox"/> Others

### RECOMMENDED CLEANING INSTRUCTIONS



### DESCRIPTIVE FEATURES

Origin of fabric	<input type="checkbox"/> EU	<input type="checkbox"/> non-EU
Product composition	<b>100% PES TREVIRA CS</b>	Weave <b>SATIN</b>
Warp repeat cm		Weft repeat cm
Weight linear mt.	<b>651</b>	Weight sq. metre <b>210</b>
Average roll length mt.		Minimum roll length mt.
Fabric width with selvedge cm.		Fabric width without selvedge cm
		Useable width cm <b>305</b>

### DIMENSIONAL STABILITY

	Warp	Weft	
Steam iron	<u>110° C</u>	<u>1%</u>	<u>1%</u> <i>Din 53894</i>
Washing with water	<u>30° C</u>	<u>2%</u>	<u>2%</u> <i>ISO 5077/ISO6330</i>
Drycleaning	<u>P</u>	<u>2%</u>	<u>2%</u> <i>ISO 3175</i>

### COLOUR FASTNESS

	Light colours	Dark colours	Pastel colours	
Xenotest light	<u>5</u>	<u>3/4</u>	<u>4</u>	<i>ISO 105-B02</i>
Washing with water	<u>4/5</u>	<u>4/5</u>	<u>4/5</u>	<i>ISO 105-E01</i>
Drycleaning	<u>4/5</u>	<u>4/5</u>	<u>4/5</u>	<i>ISO 105-D01</i>
Dry abrasion resistance	<u>5</u>	<u>4/5</u>	<u>4</u>	<i>ISO105-X12</i>
Wet abrasion resistance	<u>4/5</u>	<u>4</u>	<u>3/4</u>	<i>ISO 105-X12</i>

### MECHANICAL CHARACTERISTICS

Resistance to Martindale test 12k/Pa	N° rubs	<b>5000</b>		<b>LIGHT USE</b>	<i>ISO 12947-2</i>
Pilling resistance	500 rubs	<u>4</u>	2000 rubs	<u>4</u>	5000 rubs <u>4</u> <i>ISO 12945</i>